

Superplasticizing admixture

### AREA OF USE

Cementol Favorit W is a specially formulate complex superplasticizer intended for the production of ready-mix and construction-site concrete. It provides high water reduction and excellent pumpability. It is robust superplasticizer less sensitive to changes in the grain distribution of aggregate.

Cementol Favorit W is less suitable for working in hot weather

Its use enables:

- reduction of mixing water content with unchanged workability of concrete,
- extended workability time,
- high initial and final compressive strengths of concrete.

We use it for:

- ready-mix concrete,
- pumped concrete,
- high performance and low porosity concrete.

It contains no chlorides or other substances that cause corrosion of reinforcing steel, so it can be used in reinforced concrete and prestressed structures without restriction.

### TECHNICAL CHARACTERISTICS

Characteristic	Declared value
Appearance	Dark brown liquid
Density, 20 °C	(1.13 ± 0.02) kg/L
pH	5.5 ± 1.0
Water-soluble chloride content [Cl <sup>-</sup> ]	Chloride free
Alkali content [Na <sub>2</sub> O equivalent]	< 3.0 %

### COMPLIANCE

**Cementol Favorit W** - superplasticizer complies with the requirements of EN 934-1 and EN 934-2 / T3.1 and T3.2

### ACTION

Superplasticizer molecules are adsorbed on the surface of cement particles. Because of the composition and shape of the molecules, cement particle aggregation is prevented, the friction force between the particles in the cement paste is reduced, and the fluidity and thus workability of the cement paste is increased.

## DOSAGE AND INSTRUCTIONS FOR USE

The recommended dose is 0.3 – 1.3 % of binder weight [0.3 – 1.3 kg per 100 kg of binder].

Lower dosages are appropriate for less demanding conventional concretes, whereas higher dosages are used for high performance and more flowable concretes with higher consistency classes.

The usual dose is 0.4 - 0.7 % by weight of cement or binder and is suitable for the most common types of concrete [pumped concrete with consistency class S3 or S4].

Dosage is determined by a variety of factors, including the type and amount of cement used, the type and grain size distribution of the aggregate, the water-cement ratio, and the requirements for the properties of fresh and hardened concrete. As a result, we recommend conducting preliminary tests with the materials that will be used to determine the optimal dosage.

Cementol Favorit W can be added to a concrete mix diluted with mixing water, or it can be added in concentrated form to an already prepared fresh concrete mix of a lower consistency class, or after we have added 70-80% of the mixing water. Mix well to distribute the admixture evenly throughout the concrete mix. The recommended wet mixing time is 3 minutes.

If a consistency correction is required before concrete prepared with Cementol Favorit W is installed, the superplasticizer can be added directly to the concrete mixer of the transport vehicle. In this case, use an admixture that has been pre-diluted with water in a 1:4 ratio [1 part Cementol Favorit W + 4 parts water], and mix for 1 minute per 1 m<sup>3</sup> of concrete, and at least 5 minutes.

Cementol Favorit W is compatible with a wide range of additives, including Cementol Delta family plasticizers, Cementol Hiperplast family hyperplasticizers, Cementol B NOVI hardening accelerator, Cementol Eta family air-entraining admixtures, and Cementol Retard family set retarders.

Cementol Favorit W **is incompatible** with Cementol Zeta family superplasticizers, hardening accelerating admixture Cementol Omega F-conc., and air-entraining admixture Cementol SPA.

Before using a higher number of admixtures in a concrete mixture, we advise prior examinations. In this case, they must be added to the concrete mixture separately [one after the other].

Stir before use.

When designing a concrete mixture, we respect the requirements and principles of the EN 206 standard: Concrete - specification, performance, production and conformity, as well as the relevant national provisions.

During concreting and curing of fresh concrete we respect the principles of good practice.

## PACKAGING

drums 50 kg, IBC containers 1 m<sup>3</sup>

## STORAGE

- The product should be stored at temperatures between +5 °C and +35 °C. We need to protect it from damage, freezing and direct sunlight.
- A properly stored product has a shelf life of at least 2 years after the date of manufacture.
- The product may still be used after the date of expiry, but the characteristics important for the intended use have to be examined.

## **HEALTH, SAFETY AND ECOLOGY**

No special measures are required when working with Cementol Favorit W. Follow the general instructions for working with chemicals: take care of cleanliness, do not eat, drink or smoke while working. After finishing work, wash hands thoroughly with water.

More information on safe handling and disposal of the product is available in the safety data sheet, which is provided on request, and is also available from the dealer or distributor where you purchased the product.

## **WARNING**

Instructions and recommendations are given based on examinations in our laboratories and experience to date. Due to specific conditions and work methods, preliminary tests are advised for every type of use, for each individual case of use of the product alone, or in combination with other admixtures.

Since we cannot influence the course of work, we cannot be held responsible for its quality!



TKK d. o. o. · Srpenica 1, 5224 Srpenica, Slovenija  
+386 [0] 5 38 41 300 | [info@tkk-group.com](mailto:info@tkk-group.com) | [www.tkk-group.com](http://www.tkk-group.com)