



SANITARY SEALANT WITH PERMANENT ELASTICITY AND EXCELLENT ADHESION TO MOST SILICATE MATERIALS (ALUMINIUM, CERAMICS, GLASS, GLAZED SURFACES, PROFILED GLASS, KLINKER AND PORCELAIN).

PROPERTIES

- Thanks to a special additive, it prevents the formation of mould on silicone.
- Does not slump in vertical joints.
- Excellent adhesion to aluminium, ceramics, glass, glazed surfaces, profiled glass, klinker and porcelain.
- Good mechanical properties.
- Resistant to atmospheric effects, UV-light and ageing.
- Resistant to various chemicals.
- Releases acetic acid during hardening.
- Wide selection of colours [see colour chart].

TESTS AND CERTIFICATES

EN 15651-1,3

CE

USE

- For sealing joints in rooms where there is a possibility of mould [bathrooms and basements], for sealing silicate materials and less stressed joints, and for installing profiled glass.

TECHNICAL DATA

Fresh sealant:

Basis		acetic acid silicone
Appearance		paste
Curing mechanism		by air humidity
Specific gravity		940 ± 10kg/m ³
Skin formation time	23 °C/50 % rel. humid.	20 min.
Hardening time	23 °C/50 % rel. humid.	3 mm/day
Resistance to flow	ISO 7390	0 mm
Application temperature		between +5 °C and +40 °C

Cured sealant:

Hardness Shore A	ISO 868	10-20
Tensile strength	ISO 8339	0.3-0.5 MPa
Module E 100%	ISO 8339	< 0.4 MPa

Elongation at break	ISO 8339	150-250 %
Tensile strength	ISO 37	> 1.2 MPa
Elongation at break	ISO 37	> 350 %
Change in volume	ISO 10563	> 10 %
Temperature resistance		between -40 °C and +150 °C

APPLICATION

Prior to use it is recommended to perform an adhesion test to verify adhesion of the sealant to the substrate.

Surface preparation:

The surface of the joint must be dry, hard, clean, dust and fat free. Remove all separated and badly attached pieces.

Joint and cartridge preparation:

- If you want joints to look nice tape the edges with a masking tape.
- Cut the cartridge at the top and screw on the nozzle, which has to be cut according to the width of the joint and placed in the gun. During work interruption release the handle on the gun and pull the piston back.
- The sealant should be applied as evenly as possible.
- At the end, use a TKK SEAL smoothing tool - a smoothing instrument, or a TKK SEAL Smoothing agent soaped finger to level the sealant before the skin starts to form. It is very important to press the sealant well against the surface to be sealed.
- Remove the masking tape before the sealant starts to harden.
- Fresh sealant and tools can be cleaned with the TKK CLEAN PROTECT tool cleaner, hardened sealant should be removed mechanically first and then with a cleaner for hardened silicone - TKK CLEAN PROTECT silicone remover or TKK CLEAN PROTECT universal cleaner.

Joint depth (mm)	Joint width (mm)				
	4	6	8	10	12
6		7,2	5,4	4,3	3,7
8			4,1	3,2	2,7
10				2,6	2,2
12					1,8

The table shows how many linear metres of joints we can seal with one 260 ml cartridge relative to the width and depth of the joint.

PACKAGING

- 260 ml cartridge.
- 200 l drum.
- 600 ml, 400 ml, 300 ml sausage.
- other packagings are available by agreement.

STORAGE

12 months in a dry and cold place under 25 °C in originally closed packaging.

HEALTH, SAFETY HANDLING AND DISPOSAL INFORMATION

Additional information on safety, safe handling instructions and personal protective equipment as well as disposal information are available in a safety data sheet. Safety data sheet is available upon request. You can also ask your TKK distributor for a copy.

WARNING

Instructions contained in this document are based on our research and experience, however, due to specific conditions and working methods we recommend that you perform preliminary tests prior to any application of our products.

TKK TKK d. o. o. · Srpenica 1, 5224 Srpenica, Slovenija
+386 [0] 5 38 41 300 | info@tkk-group.com | www.tkk-group.com